



December 1, 1980
New Information
Mailed to: E, D, C/2169/DB

B-228-1 Clear Air Drying Varnish

Westinghouse B-228-1 is a clear air dry, general purpose, phenolic varnish. Excellent adhesion to metal and mica.

Descriptive Information

Color	Clear
Non-Volatiles	55±2%
Specific Gravity	0.884 - 0.900
Viscosity (Demmler #1 @ 25° C.)	100-150 Seconds
Thinner	Xylol
Flash Point	81° F.
ASTM Drying Time @ 25° C.	2.5 Hours Max.
Recommended Cure Cycle	1.5-2.0 Hours
Dielectric Strength - Dry ..	2300 Volts/Mil
Dielectric Strength - Wet ..	1200 Volts/Mil

Packaging Information

Westinghouse B-228-1 Clear Air Drying Varnish is available in 1-gallon cans, 5-gallon pails, and 55-gallon drums.

Printed in U.S.A.

The information contained herein is intended as a guide and should not be construed as a performance guarantee as the Company has no control over the manner in which others may employ the product.

www.ElectricalPartManuals.com